



135 Newbury Street, Framingham, MA 01701

(800) 238-0001 (508) 270-1800 FAX (508) 872-1566

Website: www.aicma.com Email: info@aicma.com

Specification Sheet

ALUMINUM STEARATE

Code No.	SCN No.	CAS No.	Effective Date	Product Manager	Rev. No.	Approved By
ALSFSP	2812	97404-28-9	June 2, 2011	PWS	No. 1	MPR

CHARACTERISTICS:	Fine white powder produced from animal sourced stearic acid
-------------------------	---

SPECIFICATIONS:	Appearance	White powder
	Ash	9.5-11.5%
	Water soluble salts	1% max
	Melt point	140-150°C
	Free fatty acid	6.0% max
	Moisture	1.0% max
	Bulk density	0.25- 0.30 g/cc
	Screen analysis	
	Thru 20 mesh	100% min
	Thru 40 mesh	99% min
Thru 200 mesh	80% min	

STOCKING POINTS:	Houston, TX
-------------------------	-------------

PACKAGING:	20 kg bags, 20 bags per pallet
-------------------	--------------------------------

APPLICATIONS:	Lubricating additive, water repellent, mould release agent, anticomparting and gelling agent
----------------------	--