



# American International Chemical, Inc.

Corporate Offices: (800) 238-0001

Internet: [www.aicma.com](http://www.aicma.com) Email: [info@aicma.com](mailto:info@aicma.com)

## SPECIFICATION SHEET

### ERUCAMIDE (Finaslip-E)

Code No.	SCN No.	CAS No.	Effective Date	Product Manager	Rev. No.	Approved By
ERSFIB	2600	112-84-5	January 25, 2010	PWS	No. 1	TJK

<b>CHARACTERISTICS:</b>	Monounsaturated fatty primary amide derived from rapeseed oil
-------------------------	---

<b>SPECIFICATIONS:</b>	Appearance	Beads
	Gardner color	2 max
	Total amide purity	99% min
	Erucamide content (C22:1)	90% min
	Nitrile content	1.0% max
	Acid value	0.5 max
	Iodine value	70-80
	Melting point	80-88°C
	Moisture	0.20% max
	Date of manufacture	Report

<b>STOCKING POINTS:</b>	Houston, TX
-------------------------	-------------

<b>PACKAGING:</b>	25 kg PE bags x 4 bags/layers x 6 layers = 600 kgs (1,323 lbs) per pallet
-------------------	---

<b>APPLICATIONS:</b>	Slow bloom slip agent for surface modification of polyethylene films and polypropylene caps and closures; torque release agent for PVC plastisol metal cap liners
----------------------	---

<b>SPECIAL STORAGE INSTRUCTIONS:</b>	Material has a shelf life of 1 year from date of manufacture and should be stored below 80°F in a dry place
--------------------------------------	---