



# American International Chemical, Inc.

Corporate Offices: (800) 238-0001

Internet: [www.aicma.com](http://www.aicma.com) Email: [info@aicma.com](mailto:info@aicma.com)

## SPECIFICATION SHEET

### ERUCAMIDE Finawax-E Beads

Code No.	SCN No.	CAS No.	Effective Date	Product Manager	Rev. No.	Approved By
ERUFIB	2600	112-84-5	January 25, 2008	PWS	No. 2	RVK

<b>CHARACTERISTICS:</b>	Monosaturated fatty primary amide derived from rapeseed oil
-------------------------	---

<b>SPECIFICATIONS:</b>	Appearance	Bead
	Gardner color	2 max
	Total amide purity	98% min
	Erucamide (C <sub>22:1</sub> )	90% min
	Acid value	1.0 max
	Iodine value	70-85
	Melting point	78-88°C
	Moisture	0.5% max

<b>STOCKING POINTS:</b>	Houston, TX
-------------------------	-------------

<b>PACKAGING:</b>	20 pallets per ocean container: 25 kg PE bags; 24 bags per pallet = 600 kgs (1,323 lbs) per pallet; 500 kg sacks
-------------------	--

<b>APPLICATIONS:</b>	Slow bloom slip agent for surface modification of polyethylene films and polypropylene caps and closures; torque release agent for PVC plastisol metal cap liners.
----------------------	--

<b>SPECIAL STORAGE INSTRUCTIONS:</b>	Material has a shelf life of 1 year from date of manufacture and should be stored in a cool, dry place.
--------------------------------------	---