



American International Chemical, Inc.

Corporate Offices: (800) 238-0001

Internet: www.aicma.com Email: info@aicma.com

SPECIFICATION SHEET

ETHYLENE BIS-STEARAMIDE BEADS

| Code No. | SCN No. | CAS No. | Effective Date | Product Manager | Written By | Rev. No. | Approved By |
|----------|---------|----------|----------------|-----------------|------------|----------|-------------|
| EBSFIG | 1878 | 110-30-5 | July 25, 2006 | TJK | TJK | No. 5 | RVK |

| | |
|-------------------------|--|
| CHARACTERISTICS: | A white to tan bead that has a slight amine odor |
|-------------------------|--|

| | | |
|------------------------|---------------|----------------------|
| SPECIFICATIONS: | Acid Value | 8 max |
| | Melting Point | 140 - 145 °C |
| | Amine Value | 2 max |
| | Particle size | 35% min on a 60 mesh |
| | Ash | 0.10% max |
| | Density | 400 g/l min |

| | |
|-------------------------|-------------|
| STOCKING POINTS: | Houston, TX |
|-------------------------|-------------|

| | |
|-------------------|---|
| PACKAGING: | 25 kg polyethylene lined multiwall paper bags |
|-------------------|---|

| | |
|----------------------|--|
| APPLICATIONS: | Used as a lubricant and pigment dispersant aid for the following polymers: ABS, PVC, Polypropylene, Nylon Acetal, Polyethylene and Thermo-plastic Polyether. |
|----------------------|--|