



American International Chemical, Inc.

Corporate Offices: (800) 238-0001

Internet: www.aicma.com Email: info@aicma.com

SPECIFICATION SHEET

OLEAMIDE Finawax-OK Beads

Code No.	SCN No.	CAS No.	Effective Date	Product Manager	Written By	Rev. No.	Approved By
OLKFIB	2600	301-02-0	December 30, 2008	PWS	PWS	Original	RVK

CHARACTERISTICS:	Monosaturated fatty primary amide derived from vegetable oil
-------------------------	--

SPECIFICATIONS:	Appearance	Bead
	Gardner color	2.0 max
	Total amide purity	98.5% min
	Free fatty acid	0.2 max
	Iodine value	81-87
	Melting point	72-76°C
	Moisture	0.05% max

STOCKING POINTS:	Houston, TX
-------------------------	-------------

PACKAGING:	25 kg PE bags; 24 bags per pallet = 600 kgs
-------------------	---

APPLICATIONS:	Torque release agent for Olefin based caps and closures and PVC plastisol metal cap liners. Fast bloom slip agent for surface modification of polyethylene films and mold release for thick section polyolefin parts.
----------------------	---

SPECIAL STORAGE INSTRUCTIONS:	Store below 80°F in a dry place
--------------------------------------	---------------------------------

SHELF LIFE:	Material has a shelf life of 1 year from date of manufacture
--------------------	--