



American International Chemical, Inc.

Corporate Offices: (800) 238-0001

Internet: www.aicma.com Email: info@aicma.com

SPECIFICATION SHEET

OLEAMIDE Finawax-O Beads

Code No.	SCN No.	CAS No.	Effective Date	Product Manager	Written By	Rev. No.	Approved By
OLEFIB	2600	301-02-0	July 10, 2010	PWS	PWS	No. 2	MR

CHARACTERISTICS:	Mono-unsaturated fatty primary amide derived from vegetable oil.
-------------------------	--

SPECIFICATIONS:	Appearance	Bead
	Total amide purity	98% min
	Melting point	68-78°C
	Moisture	0.25% max
	Gardner color	2 max
	Acid value	1.0 max
	Iodine value	80-95
Oleamide C18:1 purity	70% min	

STOCKING POINTS:	Bridgeview, Il; Houston, TX
-------------------------	-----------------------------

PACKAGING:	25 kg PE bags; 24 bags per pallet = 600 kgs (1,323 lbs) per pallet
-------------------	--

APPLICATIONS:	Fast bloom slip agent for surface modification of polyethylene films and mold release for thick section polypropylene parts; torque release agent for PVC plastisol metal cap liners.
----------------------	---

SPECIAL STORAGE INSTRUCTIONS:	Material has a shelf life of 1 year from date of manufacture and should be stored below 80°F in a dry place.
--------------------------------------	--