



American International Chemical, Inc.

Corporate Offices: (800) 238-0001

Internet: www.aicma.com Email: info@aicma.com

SPECIFICATION SHEET

OLEYL PALMITAMIDE Finawax OPA

Code No.	SCN No.	CAS No.	Effective Date	Product Manager	Rev. No.	Approved By
OPAFIP	2600	-	June 4, 2008	PWS	No. 1	TJK

CHARACTERISTICS:	Secondary fatty amide derived from vegetable sources
-------------------------	--

SPECIFICATIONS:	Gardner color	5.0 max
	Acid value	3 max
	Amine value	3 max
	Melting point	62-69° C

STOCKING POINTS:	Houston, TX
-------------------------	-------------

PACKAGING:	25 kg PE bags; 24 bags per pallet = 600 kgs (1,323 lbs) per pallet
-------------------	--

APPLICATIONS:	Medium bloom slip agent for surface modification of high temperature engineering thermoplastics
----------------------	---

SHELF LIFE:	Material has a shelf life of 2 years from date of manufacture and should be stored in a dry place
--------------------	---