



American International Chemical, Inc.

Corporate Offices: (800) 238-0001

Internet: www.aicma.com Email: info@aicma.com

SPECIFICATION SHEET

STEARAMIDE Finawax-S 70 Beads

Code No.	SCN No.	CAS No.	Effective Date	Product Manager	Written By	Rev. No.	Approved By
STSFIB	2600	124-26-5	April 19, 2006	PWS	PWS	Original	TJK

CHARACTERISTICS:	Saturated fatty primary amide derived from vegetable oil
-------------------------	--

SPECIFICATIONS:	Appearance	Bead
	Stearamide content	70% min
	Gardner color	2 max
	Total amide purity	98% min
	Acid value	1.0 max
	Iodine value	1.0 max
	Melting point	100-110 °C
	Moisture	0.25% max

STOCKING POINTS:	Houston, TX
-------------------------	-------------

PACKAGING:	25 kg PE bags x 4 bags/layers x 6 layers = 600 kgs (1,323 lbs) per pallet
-------------------	---

APPLICATIONS:	Medium bloom slip agent for surface modification of polyolefins
----------------------	---

SPECIAL STORAGE INSTRUCTIONS:	Material has a shelf life of 1 year from date of manufacture and should be stored below 80°F in a dry place
--------------------------------------	---