



135 Newbury Street, Framingham, MA 01701

(800) 238-0001 (508) 270-1800 FAX (508) 872-1566

Website: www.aicma.com Email: info@aicma.com

## Specification Sheet

### STEARAMIDE Finawax S-90 powder

Code No.	SCN No.	CAS No.	Effective Date	Product Manager	Rev. No.	Approved By
STNFIP	2600	124-26-5	March 12, 2012	PWS	No. 4	MPR

<b>CHARACTERISTICS:</b>	Saturated fatty primary amide derived from vegetable oil
-------------------------	--

<b>SPECIFICATIONS:</b>	Appearance	Microbead
	Gardner color	1.5 max
	Total amide purity	98% min
	Acid value	0.8 max
	Iodine value	1.0 max
	Melting point	100-110 °C
	Moisture	0.25% max
	Stearamide content	90% min
	Manufacturing date	Report
Production site	Badlapur, India	

<b>STOCKING POINTS:</b>	Houston, TX
-------------------------	-------------

<b>PACKAGING:</b>	600 kg super sacks
-------------------	--------------------

<b>APPLICATIONS:</b>	Medium bloom slip agent for surface modification of polyolefins; additive for thermal papers
----------------------	--

<b>SPECIAL STORAGE INSTRUCTIONS:</b>	Shelf Life: 18 months, should be stored below 80°F in a dry place
--------------------------------------	---