



American International Chemical, Inc.

Corporate Offices: (800) 238-0001

Internet: www.aicma.com Email: info@aicma.com

SPECIFICATION SHEET

STEARAMIDE Finawax-S Beads

Code No.	SCN No.	CAS No.	Effective Date	Product Manager	Written By	Rev. No.	Approved By
STEFIB	2600	124-26-5	February 9, 2006	PWS	PWS	No. 1	TJK

CHARACTERISTICS:	Saturated fatty primary amide derived from vegetable oil
-------------------------	--

SPECIFICATIONS:	Appearance	Bead
	Gardner color	2.0 max
	Total amide purity	98% min
	Acid value	1.0 max
	Iodine value	1.0 max
	Melting point	95-105 °C
	Moisture	0.25% max

STOCKING POINTS:	Houston, TX
-------------------------	-------------

PACKAGING:	25 kg PE bags; 24 bags per pallet = 600 kgs (1,323 lbs) per pallet
-------------------	--

APPLICATIONS:	Medium bloom slip agent for surface modification of polyolefins
----------------------	---

SPECIAL STORAGE INSTRUCTIONS:	Material has a shelf life of 1 year from date of manufacture and should be stored below 80°F in a dry place
--------------------------------------	---