



American International Chemical, Inc.

Corporate Offices: (800) 238-0001

Internet: www.aicma.com Email: info@aicma.com

SPECIFICATION SHEET

STEARYL STEARAMIDE Finawax SSX

Code No.	SCN No.	CAS No.	Effective Date	Product Manager	Rev. No.	Approved By
SSXFIP	2600	13276-08-9	April 1, 2010	PWS	Original	TJK

CHARACTERISTICS:	A mixture of stearyl stearamide and similar molecular weight fatty acid amides
-------------------------	--

SPECIFICATIONS:	Appearance	Free-flowing white beads
	Molten gardner color	2.0 max; molten product is visually clear, non-turbid
	Melting point	92-95° C
	Acid value	5.0 max
	Total amine value	0.50 max
	Iodine value	1.0 max
	Conductivity at 110°C	0.90 µS/cm max
	Trace elements	
	Sodium	350 µg/filter max
	Calcium	350 µg/filter max
	Potassium	350 µg/filter max
	Phosphorus	350 µg/filter max
	Total Phosphorus in unfiltered bulk material	50 µg/g max
	Foreign material	Made from vegetable feedstock without phosphorus containing stabilizers. No visually observable foreign material is allowed in the shipped container. The molten product is visually clear, non-turbid.
Notification	Xerox is to be notified of any process changes, including changes in starting materials, and cleaning procedures, which are introduced by the supplier and/or when the process exceeds Supplier's process control limits.	

STOCKING POINTS:	Portland, OR, Houston, TX
-------------------------	---------------------------

PACKAGING:	25 kg PE bags; 24 bags per pallet = 600 kgs (1,322.3 lbs) per pallet 500 kg (1,102.3 lbs.) sacks
-------------------	---

APPLICATIONS:	Lubricant for surface modification of high temperature engineering thermoplastics
----------------------	---

SHELF LIFE AND STORAGE INSTRUCTIONS:	Material has a shelf life of 1 year from date of manufacture and should be stored in a dry place
---	--