



American International Chemical, Inc.

Corporate Offices: (800) 238-0001

Internet: www.aicma.com Email: info@aicma.com

SPECIFICATION SHEET

SODIUM ALUMINUM SILICATE

Code No.	SCN No.	CAS No.	Effective Date	Written	Rev. No.	Approved
SASGVP	2005	1344-00-9	October 10, 2005	TJK	No. 2	MPR

CHARACTERISTICS:	White tasteless, odorless powder, which is chemically inert. Meets FDA purity standards and FCC specifications.
-------------------------	---

SPECIFICATIONS:	Identification	
	A	To pass test
	B	To pass test
	Loss on drying (2 hr @ 105° C)	8% max.
	Loss on ignition (1050° C)	8.0-13.0%
	Chemical composition (typical)	
	SiO ₂	66-76%
	Al ₂ O ₃	9-13%
	Na ₂ O	4-7%
	Arsenic	3 ppm max.
	Lead	5 ppm max.
	pH (20% slurry)	6.5-10.5

PACKAGING:	20 kg bag, 51 bags per pallet.
-------------------	--------------------------------

APPLICATIONS:	Flow agent for seasonings, spices, powdered milk products and other powdered food products.
----------------------	---

SHELF LIFE:	Retest: 2 years from date of manufacture
--------------------	--